



*ACI HIKA G for applications requiring removal of odor and acid gases*

<b>GRADE:</b>	<b>ACI HIKA G</b>	
<b>BASE:</b>	Coconut Shell Charcoal	
<b>ACTIVATION AGENT:</b>	Steam Air	
<b>MESH:</b>	4X8 US *	ASTM D 2862
<b>CTC (BASE CARBON):</b>	50% MIN	ASTM D 3467
<b>ASH CONTENT (BASE CARBON):</b>	3% MAX	ASTM D 2866
<b>HARDNESS No.:</b>	98% MIN	ASTM D 3802
<b>BULK DENSITY:</b>	0.56 ± 0.02 g/cc	ASTM D 2854
<b>MOISTURE:</b>	5% MAX	ASTM D 2867
<b>pH:</b>	Alkaline	

\* Other mesh sizes available on request