



Specially impregnated coconut based activated carbons for superior chemisorption of formaldehyde from air

GRADE:	FORMSORB	
BASE:	Coconut Shell Charcoal	
ACTIVATION AGENT:	Steam Air	
MESH:	4 X 8 US *	
HARDNESS No.	97% MIN	ASTM D3802
ASH CONTENT (BASE CARBON):	3% MAX	ASTM D2866
MOISTURE:	15% MAX	ASTM D2867

* Other mesh sizes available on request