



*Coconut shell charcoal based activated carbons impregnated with sulphur for the removal of mercury from air and natural gas*

<b>GRADE:</b>	<b>HGSORB</b>	
<b>BASE:</b>	Coconut Shell Charcoal	
<b>ACTIVATION AGENT:</b>	Steam Air	
<b>MESH:</b>	4 X 8 US *	ASTM 2862
<b>CTC (BASE CARBON):</b>	55 – 60 % MIN	ASTM D3467
<b>IODINE No. (BASE CARBON):</b>	1050 MIN	ASTM D4607
<b>BULK DENSITY:</b>	0.62 ± 0.02 g/cc	ASTM D2854
<b>HARDNESS No.</b>	97% MIN	ASTM D3802
<b>ASH CONTENT (BASE CARBON):</b>	3% MAX	ASTM D2866
<b>MOISTURE:</b>	10% MAX	ASTM D2867

\* Other mesh sizes available on request